Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 08/06/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 13-05-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 08/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M25	11/05/2020	08/06/2020	151.95 X 149.08 X 151.95	22652	**8.770**	630.5	27.8	27.6
2	Copping Concrete	M25	11/05/2020	08/06/2020	151.04 X 149.18 X 151.03	22532	**8.832**	591.7	26.3	
3	Copping Concrete	M25	11/05/2020	08/06/2020	151.85 X 151.78 X 150.28	23049	**8.853**	664.2	28.8	

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig. Date

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 18/05/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 13-05-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/05/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M25	11/05/2020	18/05/2020	149.31 X 149.93 X 151.64	22386	**8.330**	521.8	23.3	22.7
2	Copping Concrete	M25	11/05/2020	18/05/2020	150.08 X 151.57 X 151.10	22748	**8.725**	512.3	22.5	
3	Copping Concrete	M25	11/05/2020	18/05/2020	150.19 X 149.52 X 150.42	22457	**8.601**	497.3	22.1	

Sri Anjaneyulu J.S

A.E.E. (Project)

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 18/05/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 13-05-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/05/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M25	11/05/2020	18/05/2020	151.21 X 149.96 X 152.00	22675	**8.330**	523.2	23.1	22.7
2	Copping Concrete	M25	11/05/2020	18/05/2020	151.47 X 150.51 X 149.34	22797	**8.725**	504.2	22.1	
3	Copping Concrete	M25	11/05/2020	18/05/2020	149.95 X 149.50 X 150.88	22417	**8.601**	514.8	23.0	

for An Investigation
A.E.E. (Project)

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 08/06/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 13-05-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 08/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M25	11/05/2020	08/06/2020	150.89 X 149.22 X 150.32	22516	**8.770**	608.2	27.0	27.4
2	Copping Concrete	M25	11/05/2020	08/06/2020	150.85 X 151.15 X 150.43	22801	**8.832**	611.1	26.8	
3	Copping Concrete	M25	11/05/2020	08/06/2020	150.46 X 149.88 X 150.75	22550	**8.853**	638.1	28.3	

Sri. Anjanapa T.S
Venkatesh Gowda T.P
A.E.E. (Project)

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/2017

TEST REPORT FOR SAND MASONRY MORTARS

Lab ID : **CP-2020-06-17-04** **Date: 18-05-20**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 14-05-20

Sample Type : Fine Aggregate, M.Sand for Mortar

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2116-1980 (RA-2007) (Specification for Sand for Masonry Mortars)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 14-05-20

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS: 2116-1980 (RA-2007)
1	4.75 mm	0	0	0	100	100
2	2.36 mm	85	85	8.5	91.5	90-100
3	1.18 mm	200	285	28.5	71.5	70-100
4	600 micron	146	431	43.1	56.9	40-100
5	300 micron	116.5	547.5	54.8	45.3	5-70
6	150 micron	412.5	960	96.0	4.0	0-15
7	Pan	40	1000	100.0	0.0	0

CIVIL PRO Sig..... Date..... BANGALORE

TEST REPORT FOR SAND MASONRY MORTARS

Lab ID : **CP-2020-06-17-04** **Date: 18-05-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	3.18	_
2	Specific Gravity	2.51	_
3	Material finer than 75 micron(%)	12.2	Crushed Fine aggregate Max 15%
4	*Compacted Bulk Density (Kg/litre)	1.90	_
5	*Loose Bulk Density (Kg/litre)	1.73	_

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/2017

TEST REPORT FOR PLASTER SAND

Lab ID : **CP-2020-06-17-04** **Date: 18-05-20**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 14-05-20

Sample Type : Plaster Sand

Reference to BIS codes : IS: 383 : 2016 (Specification for Coarse and fine Aggregates)
IS1542:1992 (Sand for Plaster - Specification)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 14-05-20

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS: 2116-1980 (RA-2007)
1	10 mm	0	0	0	100	100
2	4.75 mm	35	35	3.5	96.5	95-100
3	2.36 mm	15	50	5	95	95-100
4	1.18 mm	50	100	10	90	90-100
5	600 micron	100	200	20	80	80-100
6	300 micron	215	415	41.5	58.5	20-65
7	150 micron	500	915	91.5	8.5	0-15
8	Pan	85	1000	100	0	---

CIVIL Pro
Sig.....
Date.....
BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2020-06-17-04** **Date: 18-05-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.8	–
2	Specific Gravity	2.56	–
3	Material finer than 75 micron(%)	8.5	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

CIVIL Pro Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 18/05/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 13-05-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/05/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M25	11/05/2020	18/05/2020	151.76 X 151.84 X 149.60	23044	**8.330**	540.7	23.5	22.7
2	Copping Concrete	M25	11/05/2020	18/05/2020	150.97 X 151.91 X 151.63	22933	**8.725**	517.0	22.5	
3	Copping Concrete	M25	11/05/2020	18/05/2020	150.75 X 149.87 X 150.87	22593	**8.601**	497.2	22.0	

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 08/06/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 13-05-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 08/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M25	11/05/2020	08/06/2020	149.08 X 149.60 X 149.34	22302	**8.770**	624.4	28.0	27.7
2	Copping Concrete	M25	11/05/2020	08/06/2020	149.01 X 151.01 X 150.91	22502	**8.832**	591.9	26.3	
3	Copping Concrete	M25	11/05/2020	08/06/2020	151.07 X 149.33 X 150.12	22560	**8.853**	648.1	28.7	

FOR CIVIL Pro.

CIVIL Pro Sig. Date. ILORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 18/05/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 13-05-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/05/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M25	11/05/2020	18/05/2020	149.96 X 151.98 X 150.06	22791	**8.330**	537.6	23.6	22.9
2	Copping Concrete	M25	11/05/2020	18/05/2020	151.13 X 151.61 X 149.70	22912	**8.725**	522.6	22.8	
3	Copping Concrete	M25	11/05/2020	18/05/2020	151.83 X 149.74 X 149.86	22734	**8.601**	506.4	22.3	

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 08/06/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 13-05-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 08/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M25	11/05/2020	08/06/2020	149.14 X 151.14 X 151.75	22542	**8.770**	612.4	27.2	27.4
2	Copping Concrete	M25	11/05/2020	08/06/2020	151.66 X 150.06 X 151.07	22758	**8.832**	602.9	26.5	
3	Copping Concrete	M25	11/05/2020	08/06/2020	151.37 X 150.99 X 151.37	22856	**8.853**	655.1	28.7	

CIVIL Pro Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 18/05/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 13-05-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/05/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M25	11/05/2020	18/05/2020	150.36 X 151.09 X 151.38	22717	**8.330**	527.9	23.2	22.6
2	Copping Concrete	M25	11/05/2020	18/05/2020	151.43 X 151.51 X 151.02	22943	**8.725**	512.7	22.3	
3	Copping Concrete	M25	11/05/2020	18/05/2020	151.60 X 149.91 X 150.26	22726	**8.601**	503.3	22.1	

CIVIL Pro Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 14/03/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 09-03-20

Customer ID : Retaining Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 14/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Retaining Wall Concrete	M25	07/03/2020	14/03/2020	151.24 X 149.37 X 151.02	22590	**8.330**	528.5	23.4	22.9
2	Retaining Wall Concrete	M25	07/03/2020	14/03/2020	150.42 X 150.99 X 150.57	22712	**8.725**	510.6	22.5	
3	Retaining Wall Concrete	M25	07/03/2020	14/03/2020	151.25 X 150.65 X 149.06	22785	**8.601**	519.7	22.8	

FOR CIVIL Pro.

CIVIL Pro Sig..... Date.....

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 04/04/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 09-03-20

Customer ID : Retaining Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 04/04/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Retaining Wall Concrete	M25	07/03/2020	04/04/2020	151.14 X 151.88 X 151.83	22955	**8.770**	625.2	27.2	27.4
2	Retaining Wall Concrete	M25	07/03/2020	04/04/2020	150.33 X 150.32 X 150.57	22599	**8.832**	598.1	26.5	
3	Retaining Wall Concrete	M25	07/03/2020	04/04/2020	149.80 X 149.98 X 151.89	22467	**8.853**	638.5	28.4	

FOR CIVIL Pro.

CIVIL Pro Sig..... Date.....

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****